

65 Years of
Precision Strip Metal Processing

Knight
Group



Please find below details of the Alloy Adjustment Factor (AAF) applicable for :-

July 2016

Grade	European Designation Number	Alloy Adjustment Factor (AAF)/KG
301	1.4310	£0.823
304S15/16/31/11	1.4301/1.4307	£0.868
304S11 (304L 10Ni)	1.4306	£0.946
305	1.4303	£1.074
316S11 (316L low mo)	1.4404	£1.269
(316L high mo)	1.4435	£1.415
316Ti	1.4571	£1.289
321/526	1.4541	£0.945
430	1.4016	£0.416

Head Office (Metal Supplies)

Knight Strip Metals
Linkside, Summit Road
Cranborne Ind Estate
Potters Bar, Hertfordshire
EN6 3JL
United Kingdom

UK Sales: 08456 447 977
International Sales +44 (0) 1707 650251
Main Office : +44(0)1707 650251
Fax: +44(0)1707 651238

Metal Processing Centre

Knight Strip Metals
Saltley Business Park
Cumbria Way, Saltley
Birmingham
B8 1BH
United Kingdom

Telephone: +44 (0)121 322 8400

Fax: +44 (0)121 322 8401